

## Technical Data Sheet - DEGALAN<sup>®</sup> 4792 L

### Binder for Heat Seal Lacquers and Printing Inks

Organic solution of an acrylic polymer based on ethyl methacrylate

#### Typical Properties

Property	Value	Unit	Method
Solvent	methyl ethyl ketone		
Solid content	53 - 57	%	DIN EN ISO 3251
Dynamic viscosity (23 °C)	1,500 - 4,000	mPas	DIN ES ISO 3219
Glass transition temperature (T <sub>g</sub> )	48	°C	DIN EN ISO 11357-1
Viscosity number	40	cm <sup>3</sup> /g	DIN EN ISO 1628-1
Molecular weight (M <sub>w</sub> )	80,000	g/mol	DIN 55672-1
Density	0.97	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Flash point	- 4	°C	DIN EN ISO 1523

#### Applications

Binder for heat-seal lacquers, especially easy-opening systems for sealing aluminium foil to PVC and polystyrene for food packaging, as well as for manufacturing printing inks for plastic films and coatings for plastics.

#### Instruction for use

Drying	After brief airing, 15 seconds at 180 °C under lab conditions.
Dilutability	DEGALAN <sup>®</sup> 4792 L can be diluted with esters, ketones and aromatic compounds. It can be blended with alcohols.
Compatibility	DEGALAN <sup>®</sup> 4792 L is compatible with nitrocellulose, cellulose acetobutyrate, various vinyl resins and most plasticizers. It is incompatible with most alkyd, urea and melamine resins.
Hints for application	In order to ensure the adhesion to aluminium foil, the latter should be primed (1 - 2 g per sqm dry film thickness) with a PVC copolymer, e.g. Vinnol <sup>®</sup> H 15/45 M from Wacker Chemie or in combination with the ration of 80/20 (solid to solid). Recommended film thickness of DEGALAN <sup>®</sup> 4792 L is 7 g per sqm.

Evonik Resource Efficiency GmbH  
 Kirschenallee  
 64293 Darmstadt  
 Germany  
 PHONE +49 6151 18-4716  
 FAX +49 6151 18-4955

Evonik Degussa Corporation  
 299 Jefferson Road  
 Parsippany,  
 NJ 07054 USA  
 PHONE +001 973 929-8000

Evonik Degussa (China) Co., Ltd.  
 55 Chundong Road,  
 Xinzhuang Industry Park  
 Shanghai 201108, China  
 PHONE +86 21 61191-027  
 FAX +86 21 61191-534

Technical Data Sheet  
 17.08.2017  
 DEGALAN 4792 L e  
 Page 1/2

## Technical Data Sheet - DEGALAN® 4792 L

### Binder for Heat Seal Lacquers and Printing Inks

Organic solution of an acrylic polymer based on ethyl methacrylate

#### General Remarks

---

Packaging	Open top steel drums: 175 kg net; Recycable IBC with PE insert: 850 kg net.
Storage	Keeps for one year after delivery date, if stored tightly closed on a cool place.

---

Typical properties are approximate reference values. If you need product specifications please contact us.

® = registered trademark

DEGALAN is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.