

Technical Data Sheet - DEGALAN[®] VP 4250 E

Binder for heat sealing lacquers

Organic dispersion of copolymers on a methacrylic esters and olefinic basis

Typical Properties

Property	Value	Unit	Method
Solvent	n-propyl acetate / ethyl acetate / isooctane 52 / 39 / 9		
Solid content	44 - 46	%	DIN EN ISO 3251
Dynamic viscosity	800 - 3,500	mPas	DIN EN ISO 3219
Glass transition temperature (Tg)	- 55, 45	°C	DIN EN ISO 11357-1
Viscosity number	144	cm ³ /g	DIN EN ISO 1628-1
Molecular weight (Mw)	255,000	g/mol	DIN 55672-1
Density	0.92	g/cm ³	DIN EN ISO 1183-1
Flash point	- 12	°C	DIN EN ISO 1523

Applications

Organic dispersion with the use as a binder for heat seal lacquers for sealing aluminium or PET film versus polypropylene, polystyrene or vinyl.

Instruction for use

Drying	After brief airing, 15 seconds at 180 °C under lab conditions.
Dilutability	DEGALAN [®] VP 4250 E is dilutable with esters and ketones.
Hints for application	In order to ensure the adhesion to aluminium foil, the latter should be primed (1 - 2 g per sqm dry film thickness) with a PVC copolymer, e.g. Vinnol [®] H 15/45 M from Wacker Chemie or in combination with the ratio of 95/5 (solid to solid). Recommended film thickness of DEGALAN [®] VP 4250 E is 7 g per sqm.

Evonik Resource Efficiency GmbH
 Kirschenallee
 64293 Darmstadt
 Germany
 PHONE +49 6151 18-4716
 FAX +49 6151 18-4955

Evonik Degussa Corporation
 299 Jefferson Road
 Parsippany,
 NJ 07054 USA
 PHONE +001 973 929-8000

Evonik Degussa (China) Co., Ltd.
 55 Chundong Road,
 Xinzhuang Industry Park
 Shanghai 201108, China
 PHONE +86 21 61191-027
 FAX +86 21 61191-534

Technical Data Sheet
 01.02.2017
 DEGALAN VP 4250 E e
 Page 1/2

Technical Data Sheet - DEGALAN® VP 4250 E

Binder for heat sealing lacquers

Organic dispersion of copolymers on a methacrylic esters and olefinic basis

General Remarks

Packaging	Open top steel drums: 175 kg net; Recycable IBC with PE insert: 850 kg net.
Storage	Keeps for one year after delivery date if stored tightly closed in a cool place. Before processing, DEGALAN® VP 4250 E must be stirred well, since storage can lead to phase separation.

Typical properties are approximate reference values. If you need product specifications please contact us.

® = registered trademark

DEGALAN is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.